

RANEBOW BROWN OXIDE

ANALYSIS	TYPICAL %
Fe ₂ O ₃	75 - 85%
CaO	2 - 4%
SiO ₂	5 - 8%
Al ₂ O ₃	1 - 3%
PYSICAL PROPERTIES	
Specific Gravity	3 - 4%
Particle Size	300 BS mesh
Oil Absorption	18ml/100gm
Matter Soluble in Water	0.5 - 0.8% max.
Light Fastness	Good
Heat Stability	Good
Resistance to Acid/Alkali	Good
APPLICATION	
Repacking	
Cement	
Blending	

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose.