

TERRACOTTA OXIDE

ANALYSIS	TYPICAL %
Fe ₂ O ₃	68 - 70%
CaO	0 - 2%
MgO	0 - 1%
SiO ₂	8 - 10%
Al ₂ O ₃	0 - 2%
PHYSICAL PROPERTIES	
Specific Gravity	3.8%
Oil Absorption	14 – 16ml/100gm
pH of 10% Slurry	8.5%
Residue on 240 mesh	5% max.
Excellent as a metal primer anti rust and in cement/concrete	
APPLICATION	
Repacking	
Cement	

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose.