



INDEPENDENT MINERAL DISTRIBUTORS (Pty) Ltd

SUPPLIERS OF INDUSTRIAL MINERALS & BASE METALS

## Product Data Sheet

### BAUXITE CHINESE ROUND KILN

Analysis	Typical %	Guaranteed
Al <sub>2</sub> O <sub>3</sub>	89.25 %	88.00 Min
SiO <sub>2</sub>	5.00 %	6.00 Max
Fe <sub>2</sub> O <sub>3</sub>	1.53 %	1.80 Max
TiO <sub>2</sub>	3.61 %	4.00 Max
K <sub>2</sub> O + Na <sub>2</sub> O	0.20 %	0.30 Max
CaO + MgO	0.30 %	0.45 Max

### Physical Properties

Density		3.30 gr/cm <sup>3</sup>	0.25 gr/cm <sup>3</sup> Min
Moisture	Lump	0.40 %	
	Mesh	0.15 %	

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose

IMD (Pty) Ltd

4 arlington road, bryanston, 2191, gauteng, south africa t: (011) 706-0322 f (011) 463-2475  
info@imdza.com www.imdza.com